



Standard Practice for Accelerated Weathering of Pressure-Sensitive Tapes by Carbon-Arc Exposure Apparatus¹

This standard is issued under the fixed designation D 3815/D3815M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This practice describes one environment for the exposure of pressure-sensitive tapes to an accelerated weathering environment.

1.2 This practice describes sample preparation and the accelerating environment to which it shall be exposed. It does not specify the length of time of the exposure nor what tests shall be performed on the material following the exposure.

1.3 The values stated in either SI or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system must be used independently without combining values in any way.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- A 666 Specification for Austenitic Stainless Steel, Sheet, Strip, Plate, and Flat Bar²
- D 3330/D3330M Test Methods for Peel Adhesion of Pressure-Sensitive Tape at 180° Angle³
- D 3715/D3715M Practice for Quality Assurance of Pressure-Sensitive Tapes³
- G 151 Practice for Exposing Nonmetallic Materials in Accelerated Test Devices that Use Laboratory Light Sources⁴
- G 152 Practice for Operating Open Flame Carbon-Arc Light Apparatus for Exposure of Nonmetallic Materials⁴

3. Summary of Practice

3.1 The pressure-sensitive tape is exposed for the time specified in accordance with the conditions provided by

Practices G 151 and G 152. Following this exposure the specimen is ready for a prescribed examination of physical characteristics by other standards as determined by the applicable material specification or other document.

4. Significance and Use

4.1 This practice does not necessarily provide direct simulation of natural weathering exposure.

4.2 Results from use of this practice shall not be represented as being equivalent to those of any natural weathering test until a satisfactory degree of correlation has been established for the material in question.

4.3 Variations in results are possible when the operating conditions vary within the accepted limits for the instrument specified in Practices G 151 and G 152.

5. Apparatus

5.1 *Exposure Apparatus*, conforming to Practices G 151 and G 152.

5.2 *Panels*, for holding or supporting the specimens approximately 75 by 225 mm [3 by 9 in.] and rigid enough to resist deforming during use.

5.2.1 The material shall be Type 302 or 304 stainless steel in accordance with Specification A 666 having a bright annealed finish. The surface roughness height shall be 50 ± 5 mm [2.0 ± 0.1 μ-in.] arithmetical average deviation from the mean line.

5.2.2 Other dimensions or materials and finishes are acceptable when defined by the subsequent test standard or commodity specification.

5.2.3 A panel or frame of the dimensions required by the exposure apparatus may be used to support the specimen panel when it is more convenient to do so, as long as the light and water paths are not interrupted or shortened by doing so.

5.3 *Rubber-Covered Roller*, at least as wide as the specimen with any diameter and rubber hardness.

6. Sampling

6.1 Sampling shall be in accordance with the requirements of the applicable material or commodity specification.

6.2 Lacking the previously mentioned specification, sampling shall be in accordance with the physical property method applicable to the testing to follow the exposure.

¹ This practice is under the jurisdiction of ASTM Committee D-10 on Packaging and is the direct responsibility of Subcommittee D10.14 on Tape and Labels.

Current edition approved Oct. 10, 1999. Published December 1999. Originally published as D 3815 – 79. Last previous edition D 3815 – 89 (1994)^{ε2}.

² *Annual Book of ASTM Standards*, Vols 01.03, 01.04 and 01.05.

³ *Annual Book of ASTM Standards*, Vol 15.09.

⁴ *Annual Book of ASTM Standards*, Vol 14.02.

6.3 When no other sampling requirement is applicable, sampling shall be in accordance with Practice D 3715/D 3715M.

7. Test Specimens

7.1 The test specimen dimensions shall be in accordance with the standard to be used subsequent to this exposure or the commodity specification.

7.2 Unwind and discard at least three, but no more than six, outer wraps of tape from the sample roll before taking specimens for testing.

7.3 Remove specimens from a freely rotating roll at the rate of 500 to 750 mm [20 to 30 in.]/s. Where width or other factors causing a high adherence to backing make it impossible to remove the specimen at the prescribed rate, remove it at a rate as close to 500 mm [20 in.]/s as possible.

8. Procedure

8.1 Apply the specimen as directed by the standard to be used subsequent to this exposure. If none, apply the specimen, centered lengthwise, to the panel using the rubber-covered roller (5.3), holding the specimen so that the roller causes the first contact of specimen with the panel.

8.1.1 When a test, such as in Test Methods D 3330/D 3330M, is to follow this exposure, it is customary to apply the tape to the prescribed panel in accordance with Test Methods D 3330/D 3330M preparatory to the exposure and peel it without reapplication following the exposure.

8.1.2 It is usually assumed that it is the backside of the pressure-sensitive tape that is to receive the energy. Any deviation from this would be expressed by the commodity specification.

8.2 Expose the specimen to the conditions described in Method I, continuous light and intermittent water spray, of Practice G 23. Use the cycle of 102 min with light and 18 min with both light and water spray. The black body temperature shall be $63 \pm 5^{\circ}\text{C}$ [$145 \pm 9^{\circ}\text{F}$]. Apparatus equipped with means of humidification shall be operated with the humidifier turned off. The total time of exposure shall be as specified in the material specification.

8.3 Follow the instructions of the commodity specification relative to observations, physical tests, or both to be performed on the specimen following the exposure.

9. Report

9.1 In reporting data, including observations, obtained by any examination following this exposure, make reference to this practice by designation. Provide the following information:

9.1.1 Any deviation from this practice and any items referenced in the Report section of Practices G 151 and G 152, and

9.1.2 The information required by the subsequent standard.

10. Keywords

10.1 accelerated weathering; carbon-arc exposure apparatus; pressure-sensitive tape

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).