



Standard Guide for Determining Volatile and Nonvolatile Content of Driers, Drying Oils, Naval Stores, and Solvents¹

This standard is issued under the fixed designation D 4140; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide is intended to aid in the selection of the proper ASTM test method for determining the volatile and nonvolatile content of driers, drying oils, naval stores, and solvents.

NOTE 1—Test methods for determining the composition of the volatile fraction are not covered by this guide.

1.2 The test methods included are as follows:

Standard	Section	ASTM Designation
Driers	5.1	D 1644
Drying oils	5.2	D 555 D 1960
Naval stores	5.3	D 233 D 889 D 1131
Solvents	5.4	D 1353

2. Referenced Documents

2.1 ASTM Standards:

- D 16 Terminology for Paint, Related Coatings, Materials, and Applications²
- D 233 Test Methods of Sampling and Testing Turpentine³
- D 555 Guide for Testing Drying Oils³
- D 804 Terminology Relating to Naval Stores, Including Tall Oil and Related Products³
- D 889 Test Method for Volatile Oil in Rosin³
- D 1131 Test Methods of Testing Rosin Oils³
- D 1353 Test Method for Nonvolatile Matter in Volatile Solvents for Use in Paint, Varnish, Lacquer, and Related Products⁴
- D 1644 Test Methods for Nonvolatile Content of Varnishes²
- D 1960 Test Method for Loss on Heating of Drying Oils³

3. Terminology

3.1 Definitions:

3.1.1 *drier*—a composition that accelerates the drying of oil, paint, printing ink, or varnish. Driers are usually metallic

compositions and are available in both solid and liquid forms (from Terminology D 16).

3.1.2 *drying oil*—an oil that possesses to a marked degree the property of readily taking up oxygen from the air and changing to a relatively hard, tough, elastic substance when exposed in a thin film to the air (from Terminology D 16).

3.1.3 *naval stores*—chemically reactive oils, resins, tars, and pitches derived from the oleoresin contained in, exuded by, or extracted from trees chiefly of the pine species (*Genus Pinus*), or from the wood of such trees (from Terminology D 804).

4. Significance and Use

4.1 The nonvolatile content of raw materials may be used to determine the total nonvolatile content (solids) of paint and related coatings. Such information may be useful to coatings producers and users for the determination of the total solids available for film formation and for the estimation of the volatile organic content.

5. Procedure

5.1 *Driers*—Most liquid driers for use in paints and varnishes are sold as solutions, so usually contain significant amounts of solvent. Use Method A in Test Methods D 1644 to determine the nonvolatile content.

5.2 *Drying Oils*—Test Method D 1960 covers the determination of moisture and any other material that is volatile under the conditions of the test. It is applicable to all natural drying oils. This method should be used only for gross contamination with volatile materials. It is not a true loss measure since small amounts of oxygen in the inert gas used will be absorbed by the oil, resulting in a small gain in weight that may more than offset small losses.

5.3 Naval Stores:

5.3.1 *Rosin*—Test Method D 889 covers the determination of the volatile oil content of rosin or similar material. The oil may consist of naturally occurring terpene oil or of foreign nonterpene oil resulting from incomplete removal of solvent used to extract the resin from wood or still wastes.

5.3.2 *Rosin Oils*—Test Methods D 1131, Section 9, covers the determination of volatile matter in rosin oils. The term “rosin oil” includes the oils obtained by dry destructive distillation of rosin, with or without subsequent redistillation,

¹ This guide is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.21 on Chemical Analysis of Paints and Paint Materials.

Current edition approved June 25, 1982. Published August 1982.

² Annual Book of ASTM Standards, Vol 06.01.

³ Annual Book of ASTM Standards, Vol 06.03.

⁴ Annual Book of ASTM Standards, Vol 06.04.

and also certain compounded oils prepared from a rosin oil base.

5.3.3 *Turpentine*—Test Methods D 233, Sections 20 through 22, cover the determination of the evaporation residue of turpentine.

5.3.4 *Other Naval Stores*—Procedures for determination of volatile and nonvolatile content of naval stores not specified in 5.3.1 through 5.3.3 should be agreed upon between the producer and the user.

5.4 *Solvents*—Test Method D 1353 covers the determination of the nonvolatile matter in volatile solvents for use in paint and related coatings and materials.

6. Precision

6.1 Some of the referenced ASTM standards have precision limits. Reference to the individual standards for precision statements is recommended.

7. Keywords

7.1 driers; drying oils; naval stores; nonvolatile; nonvolatile content; solvent

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).