



## Standard Terminology for Composite Materials<sup>1</sup>

This standard is issued under the fixed designation D 3878; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 These definitions cover generic terms, including terms of commercial importance, that appear in one or more standards on composites containing high-modulus (greater than 20-GPa ( $3 \times 10^6$  psi)) fibers.

1.2 The definitions cover, in most cases, special meanings used in the composites industry. No attempt has been made to include common meanings of the same terms as used outside the composites industry.

1.3 Definitions included have, in general, been approved as standard.

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

D 123 Terminology Relating to Textiles

2.2 *Military Standard*:

MIL-HDBK-17<sup>3</sup>

### 3. Terminology

3.1 *Definitions*:

**$\pm 45^\circ$  laminate**—a balanced symmetric laminate composed of only  $+45^\circ$  plies and  $-45^\circ$  plies.

**angleply laminate**—any balanced laminate consisting of plus and minus theta plies where theta is an acute angle with respect to a reference direction.

**balanced laminate**—any laminate that contains one ply of minus theta orientation with respect to the laminate principal axis for every identical ply with a plus theta orientation.

**braided fabric**—see *braided fabric* under **fabric**.

**breather string,  $n$** —a string, composed of a material such as glass, that provides a vacuum path from the laminate to a breather.

**bundle**—a general term for a collection of essentially parallel filaments.

**carbon fiber precursor**—a material from which carbon fiber is made by pyrolysis. Polyacrylonitrile, rayon, or pitch fibers are commonly used precursors.

**catenary:**

*filament catenary*—the difference in length of the filaments in a specified length of tow, end, or strand as a result of unequal tension; the tendency of some filaments in a taut horizontal tow, end, or strand to sag lower than others.

*roving catenary*—the difference in length of the ends, tows, or strands in a specified length of roving as a result of unequal tension; the tendency of some ends, tows, or strands in a taut horizontal roving to sag lower than others.

**caul,  $n$** —a flat or contoured tool used to distribute pressure and to define a surface for the top of the laminate during laminate consolidation or cure.

**composite:**

*composite material*—a substance consisting of two or more materials, insoluble in one another, which are combined to form a useful engineering material possessing certain properties not possessed by the constituents.

**DISCUSSION**—a composite material is inherently inhomogeneous on a microscopic scale but can often be assumed to be homogeneous on a macroscopic scale for certain engineering applications. The constituents of a composite retain their identities: they do not dissolve or otherwise merge completely into each other, although they act in concert.

*discontinuous fiber-reinforced composite*—any composite material consisting of a matrix reinforced by discontinuous fibers. The fibers may be whiskers or chopped fibers.

*fabric-reinforced composite*—any composite material consisting of a matrix reinforced by fabric (woven, knitted, or braided assemblages of fibers).

*fiber-reinforced composite*—any composite material consisting of a matrix reinforced by continuous or discontinuous fibers.

<sup>1</sup> These definitions are under the jurisdiction of ASTM Committee D30 on Composite Materials and are the direct responsibilities of Subcommittee D30.01 on Editorial and Resource Standards.

Current edition approved May 1, 2004. Published June 2004. Originally approved in 1981. Last previous edition approved in 2004 as D 3878 – 04.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from ASTM International as *The Composite Materials Handbook—MIL 17*. Also available as *MIL-HDBK-17* from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094

*filamentary composite*—a composite material reinforced with continuous fibers.

*unidirectional fiber-reinforced composite*—any fiber-reinforced composite with all fibers aligned in a single direction.

**continuous filament yarn, *n***—two or more continuous filaments twisted into a single fiber bundle.

**crossply laminate**—a laminate composed of only 0 and 90° plies. This is not necessarily symmetric.

**dam, *n***—a solid material (such as silicone rubber, steel, or aluminum), used in processing composites, to contain the matrix material within defined boundaries or to prevent crowning of a processing bag.

**damage, *n***—*in structures and structural mechanics*, a structural anomaly in material or structure created by manufacturing or service usage.

**damage resistance, *n***—*in structures and structural mechanics*, a measure of the relationship between the force, energy, or other parameter(s) associated with an event or sequence of events and the resulting damage size and type.

DISCUSSION—Damage resistance increases as the force, energy, or other parameter increases for a given size or type of damage. Conversely, damage resistance increases as damage decreases, for a given applied force, energy, or other parameter. Damage resistance and damage tolerance are often confused. A material or structure with high damage resistance will incur less physical damage from a given event. Materials or structures with high damage tolerance may incur varying levels of physical damage but will have high amounts of remaining functionality. A damage-resistant material or structure may, or may not, be considered damage tolerant.

**damage tolerance, *n***—1) *in structures and structure materials*, a measure of the relationship between damage size and type and the level of a performance parameter, such as stiffness or strength, at which the structure or structural material can operate for a particular loading condition; 2) *in structural systems*, a measure of the ability of such systems to function at designated performance parameters (for example, magnitude, length of time, and type of loading(s)) without system failure in the presence of a particular or specified level of damage.

DISCUSSION—Damage tolerance involves, and can be provided by, a number of factors operating at a number of levels: structural material, structural, and overall system. These factors include 1) basic material ability to operate with damage present (often referred to as the residual strength aspect), 2) damage growth resistance and containment provided by material and structural considerations, and 3) system inspection and maintenance plans which allow the damage to be detected and corrected and which depend upon material, structural, and operational considerations.

Damage tolerance increases as the damage size increases for a given level of a performance parameter. Damage tolerance increases as the level of the performance parameter increases for a given damage size. Damage tolerance depends upon the type of loading which is applied. For example, the damage tolerance for a compressive load can be, and generally is, different than for the same level of tensile load.

Damage resistance is often confused with damage tolerance. Damage tolerance is directly related only to the size and type of damage while being only indirectly related to how the damage was created (see *damage resistance*). Thus, damage tolerance is distinct from damage resistance.

**debond**—a deliberate separation of a bonded joint or interface, usually for repair or rework purposes.

**debulk, *v***—to decrease voids between lamina before laminate consolidation through use of vacuum or by mechanical means.

DISCUSSION—Laminae can be debulked at ambient or elevated temperatures.

**delamination**—separation of plies in a laminate. This may be local or may cover a large area in the laminate.

**denier, *n***—a direct numbering system for expressing linear density, equal to the mass in grams per 9000 metres of yarn, filament, fiber, or other textile strand.

**disbond**—an area within a bonded interface between two adherents in which an adhesive or cohesive failure has occurred. It may occur at any time during the life of the structure and may arise from a wide variety of causes. It is sometimes used to describe an area of separation between two laminae in the finished laminate (the term “delamination” is preferred).

**discontinuous fiber**—a polycrystalline or amorphous fiber that is discontinuous within the sample or component or that has one or both ends inside of the stress field under consideration. The minimum diameter of a discontinuous fiber is not limited, but the maximum diameter may not exceed 0.25 mm (0.010 in.).

**end, *n***—*in fibrous composites*, a general term for a continuous, ordered assembly of essentially parallel, collimated filaments, with or without twist.

DISCUSSION—This term covers tow, strand, sliver, yarn, and roving. The relationship between fiber form terms is shown in Table X1.1.

**fabric**—a planar textile (Synonym: *cdth*)

*braided fabric, n*—a cloth constructed by a braiding process.

*knitted fabric, n*—a cloth constructed by a knitting process.

*nonwoven fabric, n*—a cloth constructed by bonding or interlocking, or both (but not interlacing) fiber by any combination of mechanical, chemical, thermal, or solvent means.

*plied yarn, n*—a yarn formed by twisting together two or more single yarns in one operation.

DISCUSSION—Plying, which is done in the opposite direction from the twist of each of the simple yarns, serves to counter the tendency of simple yarns to untwist.

*woven fabric, n*—a cloth constructed by a weaving process.

**fiber, *n***—one or more filaments in an ordered assemblage.

DISCUSSION—There are a number of general and specific terms that define specific types of fiber forms. The relationship between fiber form terms is shown in Table 1.

**fiber content**—the amount of fiber present in a composite expressed either as percent by weight or percent by volume. This is sometimes stated as a fraction, that is, fiber volume fraction.

**fiber volume fraction**—see **fiber content**.

**filament, *n***—a fibrous form of matter with an aspect ratio >10 and an effective diameter <1 mm. (See also **monofilament**.)

**TABLE 1 Fiber Forms**

Continuous Filaments			Discontinuous Filaments	
Twist	Twisted	Little or No Twist	Twisted	Little or No Twist
Tow, <sup>A</sup>	* <sup>B</sup>	P <sup>C</sup>	— <sup>D</sup>	—
strand, sliver				
Single yarn	P	*	P	—
Plied yarn	P	—	P	—
Roving <sup>E</sup>	*	P	—	—
end	(generic term that can be applied to any of the above)			
Chopped fiber	—	—	—	P
Whisker	—	—	(single crystal)	

<sup>A</sup> Small filament count.

<sup>B</sup> \*—Secondary/alternate definition.

<sup>C</sup> P—primary/preferred definition.

<sup>D</sup> —not applicable.

<sup>E</sup> Large filament count.

**DISCUSSION**—Filaments may be essentially continuous (aspect ratio on the order of  $10^5$  or larger) or discontinuous. Whiskers are the special case of single crystal discontinuous filaments.

**filament count**—number of filaments in the cross section of a fiber bundle.

**fill**, *n*—*in a woven fabric*, the yarn running from selvage to selvage at right angles to the warp. **MIL-HDBK-17**

**filler**—in composite materials, a primarily inert solid constituent added to the matrix to modify the composite properties or to lower cost.

**float**, *n*—*in woven fabric*, the portion of a warp (or fill) yarn that extends unbound over two or more fill (or warp) yarns.

### D 123

**gel time**, *n*—*in thermosetting polymers*, the period of time from a predetermined starting point to the onset of gelation as determined by a specific test method.

**hybrid**—(for composite materials) containing at least two distinct types of matrix or reinforcement. Each matrix or reinforcement type can be distinct because of its a) physical or mechanical properties, or both, b) material form, or c) chemical composition.

**interlaminar**—describing objects (for example, voids), events (for example, fracture), or fields (for example, stress) between the laminae of a laminate.

**intralaminar**—describing objects (for example, voids), events (for example, fracture), or fields (for example, stress) within the laminae of a laminate.

**knit**—a textile process that interlocks, in a specific pattern loop of yarn by means of needles or wires.

**knitted fabric**—See *knitted fabric* under **fabric**.

**lamina**—a subunit of a laminate consisting of one or more adjacent plies of the same material with identical orientation.

**lamina orientation**—same as **ply orientation**.

**laminate**—any fiber- or fabric-reinforced composite consisting of laminae (plies) with one or more orientations with respect to some reference direction.

**laminate coordinate axes**—a set of coordinate axes, usually right-handed Cartesian, used as reference in describing the directional properties and geometrical structure of the lami-

nate. Usually the *x*-axis and the *y*-axis lie in the plane of the laminate and the *x*-axis is the reference axis from which ply angle is measured.

**laminate midplane**—the plane that is equidistant from both surfaces of the laminate.

**laminate principal axis**—the laminate coordinate axis that coincides with the direction of maximum inplane Young's modulus.

**lay-up**, *n*—(1) the stack of plies in specified sequence and orientation before cure or consolidation; (2) the complete stack of plies, bagging material, breather material, and so on before cure or consolidation; and (3) a description of the component materials, geometry, and so on of a laminate.

**lay-up**, *v*—to stack plies of material in specified sequence and orientation.

**lay-up code**—a designation system for abbreviating the stacking sequence of laminated composites.

**mandrel**—a form, fixture, or male mold used as the base for production of a part in processes such as lay-up or filament winding.

**material form**—the contour, arrangement, and structure of an unconsolidated composite material, especially with regard to the geometry and nature of the reinforcement. Factors considered part of the material form include, but are not limited to: reinforcement diameter, reinforcement length (for discontinuous reinforcements), tow size or count, fabric areal weight, fabric style, reinforcement content, and ply thickness.

**matrix**, *n*—the continuous constituent of a composite material, which surrounds or engulfs embedded filler or reinforcement.

**matrix content**—the amount of matrix present in a composite expressed either as percent by weight or percent by volume. For polymer matrix composites this is resin content.

**mold**, *n*—the support structure that holds the laminate or lay-up during the laminate consolidation process.

**monofilament**—a continuous filament strong enough to function as a yarn in commercial textile operations or as an entity in other operations.

**nonwoven fabric**—See *nonwoven fabric* under **fabric**.

**off-axis laminate**—a laminate whose principal axis is oriented at an angle  $\theta$  other than 0 or 90° with respect to a reference direction, usually related to principal load or stress direction.

**orthotropic material**—a material in which a property of interest, at a given point, possesses three mutually perpendicular planes of symmetry, which taken together define the principal material coordinate system.

**pigment**—a substance, generally in the form of fine particles, that is substantially insoluble in the matrix and is used because of its color or decorative properties.

**plied yarn**—See *plied yarn* under **yarn**.

**ply**—(in laminar composites) the constituent single layer as used in fabricating, or occurring within a composite structure.

**ply coordinate axes**—a set of Cartesian coordinates two of which lie within the plane of the ply, one axis of which is

parallel to the principal fiber direction and the other axis perpendicular to the principal fiber direction (the third axis is through the ply's thickness).

**ply count, *n***—in *laminated composite materials*, the number of plies or laminae used to construct the composite.

**ply orientation**—the acute angle ( $\theta$ ) including  $90^\circ$  between a reference direction and the ply principal axis. The ply orientation is positive if measured counterclockwise from the reference direction and negative if measured clockwise.

**ply principal axis**—the ply coordinate axis that coincides with the direction of maximum inplane Young's modulus. For balanced weave fabric either warp or fill direction may be chosen.

**preform, *n***—a preshaped fibrous reinforcement, normally without matrix, but often containing a binder to facilitate manufacture, formed by distribution of fibers to the approximate contour and thickness of the finished part.

**prepreg**—the admixture of fibrous reinforcement and polymeric matrix used to fabricate composite materials. Its form may be sheet, tape, or tow. For thermosetting matrices, it has been partially cured to a controlled viscosity called "B stage."

**quasi-isotropic laminate**—a balanced and symmetric laminate for which a constitutive property of interest, at a given point, displays isotropic behavior in the plane of the laminate. Common quasi-isotropic laminates are  $(0/\pm 60)_s$  and  $(0/\pm 45/90)_s$ .

DISCUSSION—Usually a quasi-isotropic laminate refers to elastic properties, for which case, the laminate contains equal numbers of identical plies at  $k$  orientations such that the angles between the plies are  $180i/k$  ( $i = 0, 1 \dots k - 1$ );  $k > = 3$ . Other material properties may follow different rules. For example, thermal conductivity becomes quasi-isotropic for  $k > = 2$ , while strength properties generally are not capable of true quasi-isotropy, only approximating this behavior.

**reinforcement, *n***—in *a composite material*, the discrete constituent of a composite material, either fiber or particle, which is contained within the matrix, with a purpose of

increasing the strength, or stiffness, or both.

**resin**—a solid or pseudosolid organic material often of high molecular weight, which exhibits a tendency to flow when subjected to stress, usually has a softening or melting range, and usually fractures conchoidally.

**resin content**—see **matrix content**.

**roving, *n***—in *fibrous composites*, large filament count tow. (See also **tow** and **filament count**.)

**satín, *adj***—description of a weave pattern in which warp yarns pass unbound ("float") over several fill yarns before crossing under a single fill yarn.

DISCUSSION—A satín weave is characterized by parallel fibers and no diagonal pattern.

**selvage, *n***—the woven edge portion of a fabric parallel to the warp.

**single yarn**—See *single yarn* under **yarn**.

**stacking sequence**—the arrangement of ply orientations and material components in a laminate specified with respect to some reference direction.

**staple, *n***—a collection of discontinuous filaments of spinnable length that are natural, manufactured directly in a short length, or cut from continuous filaments.

*strand*—in *fibrous composites*, Synonym for tow.

**symmetric laminate**—a laminate in which the stacking sequence for the plies located on one side of the geometric midplane are the mirror image of the stacking sequence on the other side of the midplane.

**tab, *n***—a piece of material used to hold the laminate specimen in a grip or fixture for testing so that the laminate is not damaged and is adequately supported.

**textile, *n***—a general term applied to fibers and organized assemblies of fibers with sufficient integrity to retain the organization.

DISCUSSION—Originally limited to woven fabrics, this term is now also applied to fibers, yarn intermediates, yarns, woven and nonwoven fabrics, braids, knits, and preforms, as illustrated in Fig. 1.




FIG. 1 Illustration of Textile Relationships

**thermoplastic**—a plastic that repeatedly can be softened by heating and hardened by cooling through a temperature range characteristic of the plastic, and that in the softened state can be shaped by flow into articles by molding or extrusion.

**thermoset**—a class of polymers that, when cured using heat, chemical, or other means, changes into a substantially infusible and insoluble material.

**tow**—*in fibrous composites*, a continuous, ordered assembly of essentially parallel, collimated filaments, normally without twist and of continuous filaments (Synonyms: strand and silver).

**twist, n**—*in fibrous composites*, a measure of the number of turns per unit length a fiber bundle makes around its axis.

DISCUSSION—Twist is noted as being either 'S'-twist or 'Z'-twist, where the shape of the letters are used as a mnemonic to describe the direction of the twist. Following the right-hand rule along the axis of the fiber bundle, 'Z'-twist is a positive twist and 'S'-twist is a negative twist. In addition, 'U' is often used to represent no twist (untwisted) and 'N' no twist (never twisted).

**void**—any pocket of enclosed gas or air within a composite.

**void content, n**—the volume percentage of voids in a composite.

**warp, n**—(1) the yarn running lengthwise in a woven fabric;

(2) a group of yarns in long lengths and approximately parallel, put on beams or warp reels for further textile processing including weaving, knitting, twisting, dyeing, and so forth. **D 123**

**warp nested, adj**—laid up so that warp plies alternate in the pattern: warp surface up, warp surface down.

**warp surface, n**—the ply surface that shows the larger area of warp tows with respect to fill tows.

DISCUSSION—Fabrics in which both surfaces show an equal area of warp tows with respect to fill tows do not have a warp surface.

**weave, v**—interlaces, in a specific pattern, strands or yarns oriented in two or more directions in a planar textile process.

**winding**—a process in which continuous material is applied under controlled tension to a form in a predetermined geometric relationship to make a structure. A matrix material to bind the fibers together may be added before, during or after winding. Filament winding is the most common type.

**woven fabric**—See *woven fabric* under **fabric**.

**yarn**—*in fibrous composites*, a continuous, ordered assembly of essentially parallel, collimated filaments, normally with twist, and of either discontinuous or continuous filaments.

*single yarn, n*—an end in which each filament follows the same twist.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*