



Standard Specification for Coal Tar Roof Cement, Asbestos Containing¹

This standard is issued under the fixed designation D 4022; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

ϵ^1 NOTE—Editorially switched from English dominant to SI dominant.

1. Scope

1.1 This specification covers coal tar roof cement suitable for trowel application in coal tar roofing and flashing systems.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

D 4 Test Method for Bitumen Content²

D 95 Test Method for Water in Petroleum Products and Bituminous Materials by Distillation³

D 140 Practice for Sampling Bituminous Materials⁴

D 2822 Specification for Asphalt Roof Cement²

D 3143 Test Method for Flash Point of Cutback Asphalt with Tag Open-Cup Apparatus⁴

D 3409 Test Method for Adhesion of Asphalt-Roof Cement to Damp, Wet, or Underwater Surfaces²

3. Materials and Manufacture

3.1 Coal tar roof cement shall consist of a processed coal tar base, volatile solvents, and mineral fillers including asbestos fibers, mixed to a smooth, uniform consistency suitable for trowel application.

4. Composition

4.1 The composition of coal tar roof cement shall conform to the requirements prescribed in Table 1.

TABLE 1 Composition of Coal Tar Roof Cement

	min	max
Water, volume %	...	1.0
Nonvolatile matter, mass %	65	...
Insoluble matter, mass %	15	40

5. Performance Requirements

5.1 *Uniformity*—A thoroughly stirred sample shall show no separation of solvent or settling that cannot be overcome by moderate stirring after standing for 72 h at room temperature in a closed container.

5.2 *Workability*—The cement shall be of such a consistency that it will spread readily and permit troweling smooth coatings 1.6 to 3.2 mm ($\frac{1}{16}$ to $\frac{1}{8}$ in.) thick on vertical surfaces.

5.3 *Behavior at 60°C (140°F)*—The cement shall show no evidence of blistering, and the sag or slide shall be no greater than 6 mm ($\frac{1}{4}$ in.).

5.4 *Adhesion to Wet Surfaces*—Minimum average 75 %.

5.5 *Flash Point*—38°C (100°F) minimum.

6. Sampling

6.1 Sample the material from the original container immediately after stirring to a uniform consistency, in accordance with Practice D 140.

6.2 Restir samples to obtain uniformity immediately before withdrawing portions for individual tests.

7. Test Methods

7.1 *Water*—Test Method D 95.

7.2 *Nonvolatile Matter*—Determine nonvolatile matter in accordance with Specification D 2822, except heat the dish and contents in an oven at 105 to 110°C (221 to 230°F).

7.3 *Insoluble Matter*—Test Method D 4, Procedure No. 2.

7.4 *Behavior at 60°C (140°F)*—Specification D 2822, 9.5.

7.5 *Adhesion to Wet Surfaces*—Test Method D 3409.

7.6 *Flash Point*—Test Method D 3143.

8. Inspection

8.1 Inspection of the material shall be agreed upon between the purchaser and the supplier.

¹ This specification is under the jurisdiction of ASTM Committee D08 on Roofing, Waterproofing, and Bituminous Materials and is the direct responsibility of Subcommittee D08.05 on Solvent-Bearing Bituminous Compounds for Roofing and Waterproofing.

Current edition approved Dec. 15, 1994. Published February 1995. Originally published as D4022 – 81. Last previous edition D4022 – 81.

² *Annual Book of ASTM Standards*, Vol 04.04.

³ *Annual Book of ASTM Standards*, Vol 05.01.

⁴ *Annual Book of ASTM Standards*, Vol 04.03.

9. Rejection and Resubmittal

9.1 Failure to conform to any of the requirements prescribed in this specification may constitute grounds for rejection. In the case of rejection, the supplier shall have the right to reinspect the rejected material and resubmit the lot after removal of those packages not conforming to the requirements.

10. Packaging and Package Marking

10.1 The material shall be suitably packaged to permit acceptance by the carrier and to afford adequate protection from the normal hazards of handling and shipment.

10.2 Each container shall be plainly marked with the ASTM designation, name, brand or trademark of the manufacturer or supplier, the net contents, and wording indicating the material contains asbestos. Applicable government regulations for labeling of combustible liquids shall be followed.

11. Keywords

11.1 asbestos containing; cement; coal tar; roofing

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).