



Standard Specification for Nickel-Chromium-Molybdenum-Tungsten-Alloys (UNS N06110) Welded Pipe¹

This standard is issued under the fixed designation B 757; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers welded UNS N06110² pipe in the annealed condition (temper) for general corrosion applications.

1.2 This specification covers pipe sizes in schedules shown in Table 1.

1.3 The values stated in inch-pound units are to be regarded as the standard. The SI units in parentheses are provided for information only.

1.4 The following precautionary caveat pertains only to the test method portion, Section 13, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

E 8 Test Methods for Tension Testing of Metallic Materials³

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁴

E 38 Methods for Chemical Analysis of Nickel-Chromium and Nickel-Chromium-Iron Alloys⁵

E 213 Practice for Ultrasonic Examination of Metal Pipe and Tubing⁶

E 354 Test Methods for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys⁷

E 527 Practice for Numbering Metals and Alloys (UNS)⁸

E 571 Practice for Electromagnetic (Eddy-Current) Examination of Nickel and Nickel Alloy Tubular Products⁶

2.2 ANSI Standards:

B2.1 Pipe Threads⁹

B36.19 Stainless Steel Pipe⁹

3. Classification

3.1 *Class 1*—Welded, cold-worked, annealed, and nondestructively tested in accordance with 11.4.1.

3.2 *Class 2*—Welded, cold-worked, annealed, and nondestructively tested in accordance with 11.4.2.

4. Ordering Information

4.1 Orders for material to this specification shall include the following information:

4.1.1 *Alloy Name or UNS number.*

4.1.2 *ASTM Designation.*

4.1.3 *Dimensions:*

4.1.3.1 Pipe size (see Table 1).

4.1.3.2 Length (specific or random).

4.1.4 *Class* (see 11.4).

4.1.5 *Quantity* (feet or number of pieces).

4.1.6 *Certification*—State if certification is required (see Section 16).

4.1.7 *Samples for Product (Check) Analysis*—State whether samples for product (check) analysis should be furnished (10.2).

4.1.8 *Purchaser Inspection*—If purchaser wishes to witness tests or inspection of material at place of manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed (see Section 14).

5. Materials and Manufacture

5.1 Pipe shall be made from flat-rolled alloy by an automatic welding process with no addition of filler metal. Subsequent to welding and prior to final annealing, the material shall be cold-worked in either the weld metal only or both weld and base metal.

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Oct. 10, 2000. Published November 2000. Originally published as B 757-90. Last previous edition B 757-99.

² New designation established in accordance with ASTM E527 and SAE J1086, Recommended Practice for Numbering Metals and Alloys (UNS).

³ *Annual Book of ASTM Standards*, Vol 03.01.

⁴ *Annual Book of ASTM Standards*, Vol 14.02.

⁵ Discontinued—see 1989 *Annual Book of ASTM Standards*, Vol 03.05.

⁶ *Annual Book of ASTM Standards*, Vol 03.03.

⁷ *Annual Book of ASTM Standards*, Vol 03.05.

⁸ *Annual Book of ASTM Standards*, Vol 01.01.

⁹ Available from American National Standards Institute, 11 W. 42nd St., 13th Floor, New York, NY 10036.

TABLE 1 Dimensions of Welded Pipe^A

NOTE 1—The following table is a partial reprint of Table 1 of the American National Standard for Stainless Steel Pipe (ANSI B36.19).

NOTE 2—The decimal thicknesses for the respective pipe sizes represent their nominal wall dimensions.

Nominal Pipe Size in.	Outside Diameter in. (mm)	Nominal Wall Thickness, in. (mm)		
		Schedule 5SA	Schedule 10S	Schedule 40S
1/8	0.405 (10.29)	...	0.049 (1.25)	0.068 (1.73)
1/4	0.540 (13.72)	...	0.065 (1.65)	0.088 (2.24)
3/8	0.675 (17.15)	...	0.065 (1.65)	0.091 (2.31)
1/2	0.840 (21.34)	0.065 (1.65)	0.083 (2.11)	0.109 (2.77)
3/4	1.050 (26.67)	0.065 (1.65)	0.083 (2.11)	0.113 (2.87)
1	1.315 (33.40)	0.065 (1.65)	0.109 (2.77)	0.133 (3.38)
1 1/4	1.660 (42.16)	0.065 (1.65)	0.109 (2.77)	0.140 (3.56)
1 1/2	1.900 (48.26)	0.065 (1.65)	0.109 (2.77)	0.145 (3.68)
2	2.375 (60.33)	0.065 (1.65)	0.109 (2.77)	0.154 (3.91)
2 1/2	2.875 (73.03)	0.083 (2.11)	0.120 (3.05)	...
3	3.500 (88.90)	0.083 (2.11)	0.120 (3.05)	...
3 1/2	4.000 (101.6)	0.083 (2.11)	0.120 (3.05)	...
4	4.500 (114.3)	0.083 (2.11)	0.120 (3.05)	0.237 (6.02)
5	5.563 (141.3)	0.109 (2.77)	0.134 (3.40)	...
6	6.625 (168.3)	0.109 (2.77)	0.134 (3.40)	...

^A Schedules 5S and 10S wall thicknesses do not permit threading in accordance with the American National Standard for Pipe Threads (ANSI B2.1).

5.2 Pipe shall be furnished with oxide removed. When bright annealing is used, descaling is not necessary.

6. Chemical Composition

6.1 The material shall conform to the composition limits specified in Table 2.

6.2 If a product (check) analysis is performed by the purchaser, the material shall conform to the product (check) analysis variations in Table 3.

7. Mechanical and Other Requirements

7.1 *Mechanical Properties*—The material shall conform to the mechanical properties specified in Table 4.

7.2 *Flattening Test*—A section of pipe not less than 4 in. (102 mm) in length shall be capable of withstanding, without cracking, flattening under a load applied gradually at room temperature until the distance between the platens is five times the wall thickness. The weld shall be positioned 90° from the direction of the applied flattening force.

7.2.1 Superficial ruptures resulting from surface imperfections shall not be a cause for rejection.

TABLE 2 Chemical Requirements^A

Composition Limits, %	
UNS N06110	
Ni	51.0 min
Cr	28.0–33.0
Fe	1.0 max
Mo	9.0–12.0
W	1.0–4.0
C	0.15 max
Mn	1.0 max
Si	1.0 max
P	0.015 max
S	0.015 max
Al	1.0 max
Ti	1.0 max
Cu	0.5 max
Cb	1.0 max

^A Element may be determined arithmetically by difference.

TABLE 3 Product (Check) Analysis Chemical Composition Variations

Element	Specified Limit of Element, % incl	Variation Under min or Over max of the Specified Limit of Elements
Ni	over 40.0 to 60.0	0.35
Cr	over 25.0 to 35.0	0.25
Fe	up to 1.0	0.05
Mo	over 9.0 to 12.0	0.15
W	over 1.0 to 4.0	0.07
C	over 0.0 to 0.20	0.01
Mn	up to 1.0	0.05
Si	over 0.25 to 1.0	0.05
P	up to 0.04	0.005
S	up to 0.02	0.003
	over 0.02 to 0.06	0.005
Al	over 0.10 to 1.0	0.05
Ti	over 0.10 to 0.50	0.03
	over 0.50 to 1.0	0.04
	over 1.0 to 2.0	0.05
Cb	over 0.1 to 1.0	0.04
Cu	up to 0.50	0.03

TABLE 4 Mechanical Property Requirements

Alloy	Tensile strength min, psi (MPa)	Yield strength 0.2 % offset min, psi (MPa)	Elongation in 2 in. or 50 mm, min, %
UNS N06110	95000 (655)	45000 (310)	60

7.3 *Nondestructive Test Requirements*—Tube shall be subjected to a pressure test or nondestructive electric test at the manufacturer's option (see 13.2).

7.3.1 *Acceptance and Rejection*—Material producing a signal equal to or greater than the calibration imperfection shall be subject to rejection.

7.3.1.1 Test signals produced by imperfections that cannot be identified or produced by cracks or crack-like imperfections shall result in rejection of the pipe, subject to rework and retest. To be accepted, the material shall pass the same electric test to which it was originally subjected provided that the dimensional requirements are met.

7.3.1.2 If the imperfection is judged as injurious, the pipe shall be rejected but may be reconditioned and retested providing the dimensional requirements are met. To be accepted, retested material shall meet the original electric test requirements.

7.3.1.3 If the imperfection is explored to the extent that it can be identified as noninjurious, the material may be accepted without further test provided the imperfection does not encroach on the minimum wall thickness.

8. Dimensions and Permissible Variations

8.1 *Diameter and Wall Thickness*—Outside diameter and nominal wall thickness shall not exceed the permissible variations prescribed in Table 5.

8.1.1 Material having a specified wall thickness that is 3 % or less of the outside diameter cannot be straightened properly without a certain amount of ovality resulting in the diameter. The limits to this ovality are stated in Footnote C to Table 5.

8.2 *Straightness*—Material shall be reasonably straight and free of bends or kinks.

8.3 *Length*—Variations from the specified length shall not exceed the amounts prescribed in Table 6.

9. Workmanship, Finish, and Appearance

9.1 The material shall be uniform in quality and temper, smooth, commercially straight, and free of injurious imperfections.

10. Sampling

10.1 *Lot Definition*:

10.1.1 A lot for chemical analysis shall consist of one heat.

TABLE 5 Permissible Variations in Outside Diameter^A and Wall Thickness^B

IPS	Permissible Variations in Outside Diameter, in. (mm) ^C	
	+	–
1/8	0.005(0.13)	0.005(0.13)
1/4	0.005(0.13)	0.005(0.13)
3/8	0.0075(0.19)	0.0075(0.19)
1/2	0.0075(0.19)	0.0075(0.19)
3/4	0.010(0.25)	0.0075(0.19)
1	0.010(0.25)	0.0075(0.19)
1 1/4	0.010(0.25)	0.010(0.25)
1 1/2	0.015(0.38)	0.010(0.25)
2	0.018(0.46)	0.010(0.25)
2 1/2	0.018(0.46)	0.010(0.25)
3	0.025(0.64)	0.010(0.25)
3 1/2	0.025(0.64)	0.015(0.38)
4	0.025(0.64)	0.015(0.38)
5	0.025(0.64)	0.020(0.51)
6	0.025(0.64)	0.030(0.76)

^A These permissible variations in outside diameter apply only to material as finished at the mill before subsequent swaging, expanding, bending, polishing, or other fabricating operations.

^B Wall thickness variation shall not exceed ± 12 % of the nominal wall thickness.

^C Ovality is the difference between maximum and minimum outside diameter measured at any one cross section. There is no additional tolerance for ovality on material having a nominal wall thickness of more than 3 % of the outside diameter. On this material, the average of maximum and minimum outside diameter measurements will fall within the outside diameter tolerance shown in the table above. An additional ovality allowance of twice the outside diameter tolerance spreads shown above, applied one half plus and one half minus, is allowed for material having nominal wall thickness of 3 % or less of nominal outside diameter.

TABLE 6 Permissible Variations in Lengths^A

Outside diameter in. (mm)	Cut length, in. (mm)	
	Over	Under
Under 2 (50.8)	1/8(3)	0
2 (50.8) and over	3/16(5)	0

^A These permissible variations in length apply to pipe before bending. They apply to cut lengths up to and including 24 ft (7.3 m). For lengths over 24 ft, an additional over-tolerance of 1/8 in. (3 mm) for each 10 ft (3.0 m) or fraction thereof shall be permissible up to a maximum additional over-tolerance of 1/2 in. (12.7 mm).

10.1.2 A lot for mechanical properties and flattening testing, shall consist of all material from the same heat, nominal size (excepting length), and condition (temper).

10.2 *Test Material Selection*:

10.2.1 *Chemical Analysis*—Representative samples from each lot shall be taken during pouring or subsequent processing.

10.2.1.1 Product (check) analysis shall be wholly the responsibility of the purchaser.

10.2.2 *Mechanical Properties and Flattening Testing*—Samples of the material to provide test specimens shall be taken from such locations in each lot as to be representative of that lot.

11. Number of Tests

11.1 *Chemical Analysis*—One test per lot.

11.2 *Mechanical Properties*—One test per lot.

11.3 *Flattening*—One test per lot.

11.4 *Nondestructive*:

11.4.1 *Class 1*—Each piece in each lot shall be subjected to one of the following four tests, hydrostatic, pneumatic (air underwater), eddy current, or ultrasonic.

11.4.2 *Class 2*—Each piece in each lot shall be subjected to a leak test and an electric test as follows:

11.4.2.1 *Leak Test*—Hydrostatic or pneumatic (air underwater).

11.4.2.2 *Electric Test*—Eddy current or ultrasonic.

11.4.3 The manufacturer shall have the option to test to Class 1 or 2 and select the nondestructive test methods, if not specified by the purchaser.

12. Specimen Preparation

12.1 Tension test specimens shall be taken from material in the final condition (temper) and tested in the direction of fabrication.

12.1.1 Whenever possible, all material shall be tested in full tubular size. When testing in full tubular size is not possible, longitudinal strip specimens shall be used. In the event of disagreement when full tubular testing is not possible, a longitudinal strip specimen with reduced gage length as contained in Test Methods E 8 shall be used.

13. Test Methods

13.1 The chemical composition, mechanical, and other properties of the material as enumerated in this specification shall be determined, in case of disagreement, in accordance with the following methods:

Test	ASTM Designation
Chemical analysis	E 38, E 354 ^A
Tension	E 8

^aMethods E 38 is to be used only for elements not covered by Test Methods E 354.

13.2 Nondestructive Tests:

13.2.1 *Hydrostatic Test*—Test each piece at a pressure not exceeding 1000 psi (6.9 MPa), calculated as follows:

$$P = 2St/D, \text{ or} \quad (1)$$

$$S = PD/2t \quad (2)$$

where:

P = hydrostatic test pressure, psi or MPa;

S = allowable fiber stress as follows: UNS N06110-35000 psi (242 MPa);

t = specified wall thickness, in. or mm; and

D = specified outside diameter, in. or mm.

13.2.1.1 Hold the test pressure for a minimum of 5 s.

13.2.1.2 Make visual examination when the material is under pressure. Examine the full length of material for leaks. If any pipe shows leaks during the hydrostatic test, reject it.

13.2.2 *Pneumatic (Air Underwater) Test*—Test each piece at a pressure of 150 psi (1.05 MPa).

13.2.2.1 Hold the test pressure for a minimum of 5 s.

13.2.2.2 Make visual examination when the material is submerged and is under pressure. Examine the full length of material for leaks. If any piece shows leaks during the test, reject it.

13.2.3 *Electric Test*—Give each pipe an electric test in accordance with either Practice E 213 or Practice E 571. For eddy-current testing, the calibration pipe shall contain, at the option of the producer, any one of the following discontinuities to establish a minimum sensitivity level for rejection. The discontinuity shall be placed in the weld if visible.

13.2.3.1 *Drill Hole*—Drill a hole, not larger than 0.031 in. (0.79 mm) in diameter, radially and completely through the wall, taking care to avoid distortion of the material while drilling.

13.2.3.2 *Transverse Tangential Notch*—Using a round file or tool with a ¼-in. (6.4 mm) diameter, file or mill a notch tangential to the surface and transverse to the longitudinal axis of the material. Said notch shall have a depth not exceeding 12½ % of the specified wall thickness of the material or 0.004 in. (0.102 mm), whichever is greater.

13.2.3.3 *Longitudinal Notch*—Machine a notch 0.031 in. (0.79 mm) or less in width in a radial plane parallel to the material axis on the outside surface of the pipe to have a depth not exceeding 12½ % of the specified wall thickness of the material or 0.004 in. (0.102 mm), whichever is greater. The length of the notch shall be compatible with the testing method.

13.2.3.4 For ultrasonic testing, a longitudinal calibration notch shall be on the outside diameter and inside diameter. The depth of the notch shall not exceed 12½ % of the specified wall thickness of the material or 0.004 in. (0.10 mm), whichever is greater. Place the notch in the weld if visible.

13.3 For purposes of determining compliance with the specified limits for requirements of the properties listed in the following table, an observed value, or a calculated value shall be rounded as indicated below, in accordance with the rounding method of Practice E 29:

Test	Rounded unit for observed or calculated value
Chemical Composition and tolerances (when expressed in decimals).	Nearest unit in the last right-hand place of figures of the specified limit. If two choices are possible, as when the digits dropped are exactly a 5 or a 5 followed only by zeros, choose the one ending in an even digit, with zero defined as an even digit.
Tensile strength, yield strength	Nearest 1000 psi (6.9 MPa)
Elongation	Nearest 1 %

14. Inspection

14.1 Inspection of the material shall be agreed upon between the purchaser and the supplier as part of the purchaser contract.

15. Rejection and Rehearing

15.1 Material that fails to conform to the requirements of this specification may be rejected. Rejection should be reported to the producer or supplier promptly and in writing. In case of dissatisfaction with the results of the test, the producer or supplier may make claim for a rehearing.

16. Certification

16.1 Upon request of the purchaser in the contract or order, a manufacturer's certification that the material was manufactured and tested in accordance with this specification together with a report of the test results shall be furnished.

17. Product Marking

17.1 *Material*—The name or brand of the manufacturer, the trade name of the material or UNS number, the letters ASTM, the specification number, heat number, class, and nominal size shall be legibly stenciled on each piece ½ in. (12.7 mm) and over in outside diameter, provided the length is not under 3 ft (914 mm). The material marking shall be by any method that will not result in harmful contamination.

17.1.1 For material less than ½ in. in outside diameter and material under 3 ft in length, the information specified in 17.1 shall be either stenciled or marked on a tag securely attached to the bundle or box in which the pipe is shipped.

18. Packaging and Package Marking

18.1 Each bundle or shipping container shall be marked with the name or brand of the manufacturer, the trade name of the material or UNS number, the letters ASTM, the specification number, heat number, class and nominal size; gross, tare, and net weight; consignor and consignee address; contract or order number; or such other information as may be defined in the contract or order.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).