



Standard Specification for Rubber Floor Tile¹

This standard is issued under the fixed designation F 1344; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers requirements for the compound and physical characteristics of rubber floor tile.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 The following documents of the issue in effect on the date of this material purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards:*²

D 883 Terminology Relating to Plastics

D 1566 Terminology Relating to Rubber

D 2240 Test Method for Rubber Property—Durometer Hardness

D 3389 Test Method for Coated Fabrics Abrasion Resistance

F 141 Definitions of Terms Relating to Resilient Floor Coverings

F 373 Test Method for Embossed Depth of Resilient Floor Coverings

F 386 Test Method for Thickness of Resilient Flooring Having Flat Surfaces

F 410 Test Method for Wear Layer Thickness of Resilient Floor Coverings by Optical Measurement

F 511 Test Method for Quality of Cut of Resilient Floor Tile

F 710 Practice for Preparing Concrete Floors and Other Monolithic Floors to Receive Resilient Flooring

F 925 Test Method for Resistance to Short-Term Chemical

Exposure of Resilient Flooring

F 970 Test Method for Static Load Limit

F 1482 Guide to Wood Underlayment Products Available for Use Under Resilient Flooring

F 1514 Test Method for Measuring Heat Stability of Resilient Vinyl Flooring by Color Change

F 2055 Test Method for Size and Squareness of Resilient Floor Tile by Dial Gage Method

F 2199 Test Method for Determining Dimensional Stability of Resilient Floor Tile After Exposure to Heat

2.3 *American National Standards:*

ANSI/ASQC Z1.4 – 1993 Sampling Procedures and Tables for Inspection by Attributes³

3. Terminology

3.1 *Definitions*—For definitions of other terms used in this standard, see Terminology F 141.

4. Classification

4.1 Rubber floor tile covered by this specification shall be classified as:

Class I—Homogeneous Rubber Floor Tile

A. Solid Color

B. Through Mottled

Class II—Laminated Rubber Floor Tile

A. Solid Color Wear Layer

B. Mottled Wear Layer

4.2 The tile in 4.1 may have either smooth, embossed, or molded pattern wearing surfaces.

4.3 These products shall not contain asbestos.

5. Ordering Information

5.1 Purchaser shall state whether this specification is to be used, select the preferred options permitted herein, and include the following information in the invitation to bid or purchase order:

5.1.1 Title, number, and date of this specification.

5.1.2 Class, color, pattern, and wearing surface (see Section 4).

5.1.3 Quantity, in square feet, square metres, or cartons.

5.1.4 Size required (see 8.4).

5.1.5 Thickness required (see 8.3).

¹ This specification is under the jurisdiction of ASTM Committee F06 on Resilient Floor Coverings and is the direct responsibility of Subcommittee F06.80 on Specifications.

Current edition approved March 1, 2004. Published April 2004. Originally approved in 1991. Last previous edition approved in 2003 as F 1344-03a.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

5.1.6 Overall thickness, if molded pattern tile is specified (see 8.1).

5.1.7 Base thickness, if molded pattern tile is specified (see 8.2).

5.1.8 Resistance to chemicals (see 7.4).

5.1.9 Lot formation, if other than as specified in ANSI/ASQC Z1.4–1993 (see Sections 10 and 11).

5.1.10 Sampling, if other than as specified in ANSI/ASQC Z1.4–1993 (see Sections 10 and 11).

5.1.11 Statement requesting certification, if certification of compliance is required (see Section 12).

5.1.12 Packing requirements, if other than as specified (see Section 14).

5.1.13 Palletization, if required.

5.1.14 Marking required, if other than specified (see Section 13).

5.1.15 Other requirements.

6. Materials and Manufacture

6.1 *Material*—The polymeric binder of the rubber floor tile shall (1) satisfy the definition of rubber in Terminology D 1566, and (2) have been vulcanized, as defined in Terminology D 1566 (under vulcanization), such that it becomes thermoset as defined in Terminology D 883. The rubber floor tile made from this compound shall be resistant to neutral pH cleaners.

6.2 *Color, Pattern, and Wear Layer Surface*—The color, pattern, and wear layer surface, as applicable, shall be as specified in the contract or order (see 5.1).

NOTE 1—The colors and patterns that are available are indicated in individual manufacturer’s current catalogs. As manufactured, colors may vary somewhat in hue or shade from the catalog.

NOTE 2—Where color match is a concern, samples from the manufacturer shall be obtained to verify color acceptability.

6.3 *Homogeneous Rubber Floor Tile*—The surface coloring or mottling shall be uniform throughout the entire thickness of the rubber floor tile.

6.4 *Layered Rubber Floor Tile*—The surface color or mottling need not extend through the entire thickness of the rubber floor tile, but must extend throughout the entire thickness of the wear layer.

6.4.1 The wear layer must have a minimum thickness of 0.040 in. (1.0 mm) when measured in accordance with Test Method F 410.

6.4.2 The appearance of the rubber floor tile, after removing 0.020 in. (0.51 mm) of the wear layer thickness, shall compare favorably in appearance with the rubber floor tile original appearance. The removal of the wear layer may be accomplished by any suitable method.

7. Performance Requirements

7.1 *Hardness*—The rubber floor tile shall have a durometer hardness of not less than 85 (Shore, Type A) when tested in accordance with Test Method D 2240.

7.2 *Static Load Limit*—When tested in accordance with Test Method F 970, with an applied load of 250 lb (113.4 kg), the residual indentation shall not be greater than 0.005 in. (0.127 mm).

7.3 *Resistance to Short-Term Chemical Exposure*—When tested in accordance with Test Method F 925, the rubber floor tile shall have no more than a slight change in surface dulling, surface attack, or staining when exposed to the following chemicals:

- White vinegar (5% acetic acid)
- Rubbing alcohol (70% isopropyl alcohol)
- Sodium hydroxide solution (5% NaOH)
- Hydrochloric acid solution (5% HCl)
- Sulfuric acid solution (5% H₂SO₄)
- Household ammonia solution (5% NH₄OH)
- Household bleach (5.25% NaOCl)
- Disinfectant cleaner (5% active phenol)

NOTE 3—These basic chemicals are representative of those likely to be found in domestic, commercial, and institutional use. Many proprietary compounds contain one or more of these basic chemicals. Should the rubber floor tile for an unusual application need to be resistant to a specific chemical, this additional requirement should become part of the procurement document (see 5.1.8).

NOTE 4—Since standard SBR rubber floor tiles are not recommended for installation where the product will be exposed to animal fats, vegetable oils, and petroleum-based reagents, mineral oil, olive oil, kerosene, and gasoline have been removed from the standard chemical list to eliminate any confusion regarding product selection.

7.4 *Resistance to Heat*—When tested in accordance with Test Method F 1514, the color change of the rubber floor tile shall have an average ΔE not greater than 8.0 after 7 days exposure to 158°F (70°C).

7.5 *Abrasion Resistance*—When tested in accordance with Test Method D 3389 and with the abrader equipped with H-18 wheels and a load of 500 g, the maximum material loss shall not exceed 1 gram after 1000 cycles.

7.6 *Dimensional Stability*—When tested in accordance with Test Method F 2199, the dimensional change of the rubber floor tile in both the machine direction (MD) and the across machine direction (AMD) shall not exceed 0.15 %.

7.7 *Resistance to Light*—Task group F06.80.13 will continue to search for a test method or develop a test method to address this requirement. Existing Q-UV and Xenon-Arc test methods used to test rubber floor tiles resulted in extremely high failure rates which is not typical in everyday use of these products.

8. Dimensions and Permissible Variations

8.1 *Overall Thickness*—Unless otherwise specified (see 5.1), the molded pattern rubber floor tile shall have a minimum thickness of 0.080 in. (2 mm) and shall be measured for overall thickness at the thickest cross-sectional area of the tile. The thickness of the molded pattern shall be uniform throughout the tile.

8.2 *Base Thickness*—Molded pattern rubber floor tile base thickness shall be measured at the thinnest cross-sectional area of the tile. The thinnest cross-sectional area shall be uniform throughout the tile.

8.3 *Thickness Tolerances*—Thickness shall be as specified in the contract or order (see 5.1). A total tolerance of ±0.005 in. (±0.127 mm) for smooth rubber floor tile or +0.015/–0.005



FIG. 1 Overall and Base Thickness

in. (+0.381/–0.127 mm) for molded and embossed pattern rubber floor tile, from the specified thickness shall be permitted in the base thickness alone or in combination with the overall thickness, when measured in accordance with Test Method F 386 for smooth and molded pattern rubber floor tile and Test Method F 373 for embossed pattern rubber floor tile. In case of molded and embossed pattern rubber floor tile, overall thickness and base thickness shall be reported (see Fig. 1).

8.4 *Size*—Rubber floor tiles are available in a variety of sizes and shall be specified (see 5.1). The following permissible tolerances shall be permitted per tile when measured in accordance with Test Method F 2055.

Up to and including 12 by 12 in. = ±0.016 in. (±0.4 mm).

Larger than 12 by 12 in. and up to and including 24 by 24 in. = ±0.018 in. (±0.45 mm).

Larger than 24 by 24 in. = ±0.020 in. (±0.5 mm).

8.5 *Squareness*—When tested in accordance with Test Method F 2055, the out of squareness of the rubber floor tile shall not exceed 0.010 in. (0.254 mm).

8.6 *Quality of Cut (Joint Tightness)*—When tested in accordance with Test Method F 511, the maximum width opening between the rubber floor tile edges shall not exceed 0.005 in. (0.127 mm). The maximum width opening between the rubber floor tile corners shall not exceed 0.005 in. (0.127 mm). The edges of the rubber floor tile shall not have burrs or nicks.

NOTE 5—This requirement is the responsibility of the manufacturer and is not performed after the rubber floor tiles have been installed.

9. Workmanship, Finish, and Appearance

9.1 The rubber floor tile furnished in accordance with this specification shall be an acceptable match to approved samples in color, pattern, wearing surface, and appearance. The product shall be free of defects which adversely affect performance or appearance. Such defects include: blemishes, indentations, cracks, blisters, breaks in corners or edges, and delamination.

9.2 Unless otherwise specified in the contract or order (see 5.1), the back or bonding surface of the rubber floor tile shall be buffed, roughened, ribbed, grooved, or otherwise modified

to improve the adhesive bond of the rubber floor tile, but in no case shall the thickness of the tile be decreased to the extent that any depression or groove on the bonding surface be perceptible, under any circumstances, on the exposed surface.

10. Sampling for Test

10.1 Sampling for testing physical characteristics listed in Table I shall be done in accordance with the provisions set forth in ANSI/ASQC Z1.4–1993. The inspection level shall be special inspection level S-1, as noted in Table I, and the acceptable quality level (AQL) shall be 6.5 defects per hundred units as noted in Table II-A or as otherwise specified in 10.2 herein. The lot size shall be expressed in units. A unit represents a single, manufactured, inventoried, finished tile.

10.2 Sampling for testing physical characteristics listed in Table I shall be agreed upon by the purchaser and the manufacturer as part of the procurement document.

11. Inspection

11.1 Sampling for inspection of the rubber floor tile for defects that would adversely affect performance (see 9.1) shall be done in accordance with the provisions set forth in ANSI/ASQC Z1.4–1993. The inspection level shall be Level I as noted in Table I with an acceptable quality level (AQL) of 6.5 defects per hundred as noted in Table II-A or as otherwise specified in 11.2 herein. The lot size shall be expressed in units. A unit represents a single, manufactured, inventoried, finished tile.

11.2 Inspection of the rubber floor tile for defects that would adversely affect performance (see 9.1) shall be agreed upon by the purchaser and the manufacturer as part of the procurement documents.

12. Certification

12.1 When specified in the purchase order or contract (see 5.1.11), a manufacturer’s certification and any other documents required to substantiate certification shall be furnished to the purchaser that the product was manufactured to meet this specification.

TABLE 1 Characteristics and Tests

Characteristic	Requirement	ASTM Test Method	Reference
Composition of Material		Certificate of Compliance	6.1
Wear Layer Thickness	min, 0.040 in. (1.0 mm)	F 410	6.4.1
Hardness	min 85 Shore A	D 2240	7.1
Static Load Resistance	≤0.005 in. (0.127 mm) at 250 lb (113.4 kg) load	F 970	7.2
Resistance to Short-Term Chemical Exposure	No more than a slight change in surface dulling, surface attack, or staining	F 925	7.3
Resistance to Heat	Avg. ΔE not greater than 8.0	F 1514	7.4
Abrasion Resistance	Less than 1 g loss after 1000 cycles	D 3389	7.5
Dimensional Stability	The dimensional change of the rubber floor tile in both the machine direction (MD) and the across machine (AMD) shall not exceed 0.15 %	F 2199	7.6
Thickness	as specified		
Smooth Surface Tile	±0.005 in. (±0.127 mm)	F 386	8.3
Molded Pattern Tile	+0.015/–0.005 in. (+0.381 mm/–0.127 mm)	F 386	8.3
Embossed Pattern Tile	+0.015/–0.005 in. (+0.381 mm/–0.127 mm)	F 373	8.3
Size	Up to and including 12 by 12 in. = ±0.016 in. (±0.4 mm) Larger than 12 by 12 in. and up to and including 24 by 24 in. = ±0.018 in. (±0.45 mm) Larger than 24 by 24 in. = ±0.020 in. (±0.5 mm)	F 2055	8.4
Squareness	max, 0.010 in. (0.254 mm)	F 2055	8.5
Quality of Cut	0.005 in. (0.127 mm) max	F 511	8.6

13. Product Marking

13.1 Unless otherwise specified in 5.1, shipping containers shall be marked with the name of the material as defined by the contract or order under which the shipment is made, the size, thickness, the pattern number, the quantity contained therein, and the name of the manufacturer.

13.2 When product sample sets, sample set cover cards, marketing and technical literature reference this specification, the complete product classification information relative to this specification shall be included.

14. Packaging and Packing

14.1 Unless otherwise specified in 5.1, the rubber floor tile shall be packaged in accordance with normal commercial practice and packed to ensure acceptance by common carrier and to provide protection against damage during normal shipping, handling, and storage.

15. Keywords

15.1 flooring; resilient; rubber; tile

APPENDIX

(Nonmandatory Information)

X1. ADDITIONAL INFORMATION

X1.1 The following sources can be consulted for additional information: Practice F 710 and Guide F 1482.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).